

MULTI-PURPOSE DILUENT

DIESTONE E is a solvent composition with a controlled volatility, used as a cleaning agent. It is free from halogenated hydrocarbons and is not classified as toxic, harmful or corrosive (decree of 02/21/1990, EC 88/379, 89/178, 90/35). It does not contain any teratogenic or carcinogenic components.

- Very high solvent power which gives excellent cleaning and degreasing metallic surfaces before painting.
- Non corrosive on metals.
- Efficient reactivation and cleaning of epoxy or polyurethane primers.
- Pleasant odour. Good cost/quality ratio.
- Compatible with epoxy, polyurethane, acrylic nitrocellulose paints and lacquers

USES

Painting and paint stripping shops, construction and assembly :

- Cleaning of paint application equipment (brushes, rollers, spray guns, spray booths, etc...).
- Subsidiary stripper of dry paint films (elimination of polyvinyl primers and nitrocellulose lacquers).
- Elimination of "washable" temporary protections
- Cleaning of jointing, sealant and glue application equipment
- Removal of excess quantities, marks and runs of jointing products, sealants and glues.

DIRECTIONS FOR USE

DIESTONE E can be used as supplied and without dilution at ambient temperature using the following methods:

- spraying,
- brushing or swabbing,
- by circulation in paint equipment pipes.

TECHNICAL CHARACTERISTICS

Appearance	clear liquid
Density	(at 20°C) 0.9
Flammability point	(ISO 2592) < 21°C
Evaporation rate (NFT 30301)	0.7
Halogenated hydrocarbon content	none



PRECAUTIONS FOR USE AND STORAGE

It is recommended to wear suitable gloves because the strong degreasing action of DIESTONE E will de-fat the skin. Avoid breathing or swallowing the product. Wear suitable eye protection when handling or using the product. In the case of contact with skin or eyes, rinse immediately and abundantly with water. If work is continuous, it is recommended to install a vapour evacuation system at the emission point.

DIESTONE E must be used and stored in a sufficiently ventilated place, away from flame and heat sources. The product must be protected and kept in the closed original containers.

Please read the safety data sheet for further information.

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge, they have, however, an indicative value only, and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by Socomore ; all data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact our services.



Support technique International / International Technical Support
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomore.com
Pour connaître notre correspondant le plus proche / To find our nearest correspondent
socomore@socomore.com

socomore
finishing solutions