

Acid activated gel-type aircraft stripper for all types of paint. Non corrosive on most metallic surfaces.

Main advantages :

- High efficiency on paint systems with sol-gel pre-treatment
- Reduces the overall stripping time and paint stripper consumption
- Optimal viscosity for cling ability to vertical and overhead surfaces
- Free from Chlorine, phenol & Chromate

Paint remover in acid medium intended for all paints, especially adapted to epoxy, polyurethane and alkydurethane, non corrosive on most metallic surfaces (steels, aluminium alloys, titanium, etc...) except magnesium, high strength steel and cadmium plated steel.

- Owing to its formulation, **SOCOSTRIP A0212 SR** reduces the safety and environmental risks and drawbacks usually linked to removers containing dichloromethane, phenols and chromates.
- The viscosity is adjusted in order to facilitate the application by hand or by means of "airless" apparatus and to effectively cover all surfaces, even if vertical or overhanging.

DIRECTIONS FOR USE

- **SOCOSTRIP A0212 SR** is usually applied manually, by brushing or by spraying under low pressure.
- The surfaces to be treated must be clean and dry. It is important to eliminate all soils and greases from the painted surfaces before removal; use suitable cleaners to do so such as **SYNCLAIR A/C** or **DIESTONE DLS**.
- Materials such as rubbers or plastics are attacked; therefore they must be protected if they are not to be removed.
- Temperature is an important factor. It is advised to bring the product and surface to ambient temperature; the optimum temperature for use is between 25 and 35° C (77° and 95°F).
- Application time: should remain on the surface for to 1 à 6 hours (depending on the temperature, the coating thickness and the paint system). If necessary, can be left on the surface for longer periods of time. And / or can be reapplied 2 or 3 times as required to loosen any remaining paint.
- After paint removal, rinse either by water spraying or by means of cleaning diluents **DIESTONE DLS**. In case of rinsing by water spraying, we strongly advise to operate a second rinsing for neutralization (aqueous solution of SYNCLAIR A/C - concentration 2 to 3

- %).
- Contact with austenitic stainless steel is authorised (pumps).

TECHNICAL CHARACTERISTICS

Appearance	thixotropic gel
Colour	blue
Specific gravity	(at 20°C) 1.0
Flash point	85°C (185°F)
pH	2.5

PRECAUTIONS FOR USE AND STORAGE

Keep protected from frost.

If the temperature is lower than 0°C (32°F), the properties of the product may be altered.

Shelf life: 12 months (can be used until 12 months if the gel emulsion is visually stable).

Store and transport **SOCOSTRIP A0212 SR** in a dry place protected from frost and heat (imperatively > 0°C/32°F and < 35°C/ 95°F), in the original closed packaging.

Acid pH: store with other acid chemicals.

Use the product in ventilated areas. Wear eye/face protection, safety gloves and protective clothing. In case of contamination of the skin, rinse with copious amounts of running water. In case of projection in eyes, rinse immediately and abundantly with running water.

For more information regarding the danger of the product, please consult the product safety data sheet according to local regulation.

For professional use only.

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as SOCOMORE deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Pictures are not contractual. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.